

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 607 978 B1

(12) EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
17.11.1999 Bulletin 1999/46

(51) Int Cl.⁶ C07F 9/572, A61K 9/127,
A61K 47/48, C07F 9/10

(21) Application number: 94100819.5

(22) Date of filing: 20.01.1994

(54) Phospholipid derivative and liposome containing it

Phospholipid-Derivat und sie enthaltende Liposome

Dérivé de phospholipide et liposome le contenant

(84) Designated Contracting States:
CH DE ES FR GB IT LI NL SE

(30) Priority: 22.01.1993 JP 2765193

(43) Date of publication of application:
27.07.1994 Bulletin 1994/30

(73) Proprietor: Mitsubishi Chemical Corporation
Chiyoda-ku Tokyo (JP)

(72) Inventors:

- Tagawa, Toshiaki
Yokohama-shi, Kanagawa-ken (JP)
- Awane, Kaoru
Yokohama-shi, Kanagawa-ken (JP)
- Nagaike, Kazuhiro
Kanagawa-ken (JP)

(74) Representative:
TER MEER STEINMEISTER & PARTNER GbR
Mauerkircherstrasse 45
81679 München (DE)

(56) References cited:

WO-A-92/06192 CA-A- 2 069 244

- ANTISENSE RESEARCH AND DEVELOPMENT
vol. 2, no. 3, 1992, pages 187-197 S. M. SULLIVAN
: "Inhibition of human immunode- ficiency
virus-1 proliferation by liposome- encapsulated
sense DNA to the 5' TAT splice acceptor site"
- FEBS LETTERS vol. 268, no. 1, 1990,
AMSTERDAM NL pages 235 - 237 A. L.
KLIBANOV 'Amphipathic polyethyleneglycols
effectively prolong the circulation time of
liposomes'
- BIOCHIMICA ET BIOPHYSICA ACTA vol. 1062,
no. 2, 1991, pages 142-148 A. L. KLIBANOV :
"Activity of amphipathic poly (ethylene glycol)
5000 to prolong the circulation time of
liposomes"

Remarks:

The file contains technical information submitted
after the application was filed and not included in this
specification

EP 0 607 978 B1

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 93(1) European Patent Convention).

Description

[0001] The present invention relates to a novel phospholipid derivative and a liposome containing it. Particularly, it relates to a novel phospholipid derivative having a polyalkylene glycol moiety having a maleimide group.

[0002] A liposome being a lipid vesicle is capable of containing many substances irrespective of whether such substances are water-soluble or hydrophobic and thus is expected to be a prospective carrier especially for a drug delivery system (DDS).

[0003] In recent years, for the purpose of imparting a functionality to the liposome in addition to the inherent properties thereof, an attempt has been made to bond (or introduce) a functional compound such as a protein, a peptide, a sugar or a hydrophilic polymer to the liposome surface.

[0004] On the other hand, many studies have been made to overcome general drawbacks of a liposome, such as agglomeration and non-specific capture by a reticuloendothelial system organ such as liver or spleen, and it has been found effective to bond a polyethylene glycol to the liposome (Japanese Unexamined Patent Publications No. 249717/1989 and No. 149512/1990, FEBS letters, 268,235 (1990)).


[0005] Further, for the purpose of imparting the function of protein and the properties of polyethylene glycol, methods have been proposed to produce a liposome which contains both a protein and a polyethylene glycol (BBA, 142, 1062 (1991), and Japanese Unexamined Patent Publication No. 346918/1992, and CA-A-2 069 244.

[0006] The former is a method which comprises solubilizing a lipid-modified antibody, a phospholipid, cholesterol and a lipid derivative of polyethylene glycol by means of a surfactant, followed by removing the surfactant by dialysis, to obtain a liposome. However, it is difficult to remove the surfactant completely, and the product will hardly be useful as a drug. Further, it is necessary to carry out the dialysis for a long period of time at a temperature higher than the phase transfer temperature of the lipid, whereby a useful lipid is rather limited especially when an unstable protein is employed for the production.

[0007] The latter is a method which comprises preparing a liposome containing maleimide groups, then bonding a protein having thiol groups and further bonding a polyethylene glycol having thiol groups to excess maleimide groups. While the protein can be bonded under a mild condition, this method has a problem that the production process is cumbersome, since it involves a two step reaction, and it is difficult to independently control the amount of each component to be bonded.

[0008] The present inventors have conducted a study to solve such problems of conventional liposomes containing both a protein and a polyalkylene glycol and as a result, have found it possible to readily produce a liposome containing both a protein and a polyalkylene glycol by using, as a liposome-constituting component, a phospholipid derivative having a maleimide group at one end of a polyalkylene glycol and a phosphatidylethanolamine moiety at the other end. Further, it has been surprisingly found that the liposome containing such a phospholipid derivative can readily be micronized during the process for micronizing the liposome. The present invention has been accomplished on the basis of these discoveries.

[0009] Namely, the present invention provides a phospholipid derivative of the following formula (I) and a liposome containing such a derivative:



wherein A is a residue of a phospholipid having a phosphatidylethanolamine moiety, and B is a linking group having a polyalkylene glycol moiety.

[0010] In the accompanying drawings:

[0011] Figure 1 is a graph showing the ¹H-NMR chart of M-PEG-PE obtained in Example 1.

[0012] Figure 2 is a graph showing the results of measurement of the particle size distribution of the M-PEG-PE-containing liposome prepared in Example 3 by a dynamic light scattering method.

[0013] Figure 3 is a graph showing the results of measurement of the particle size distribution of the liposome containing no M-PEG-PE, prepared in Comparative Example, by a dynamic light scattering method.

[0014] Figure 4 is a photograph showing the reactivity of the antibody-bonded liposome (immunoliposome) prepared in Example 4 to human stomach cancer cells MKN45. The observation was made by a fluorescent microscope using a fluorescent lipid integrated to the liposome, as a marker.


[0015] Figure 5 is a photograph showing the reactivity of the non-antibody-bonded liposome prepared in Comparative

Example to human stomach cancer cells MKN45. The observation was made by a fluorescent microscope using a fluorescent lipid integrated to the liposome, as a marker.

[0016] Figure 6 is a photograph showing the luminous field image of Figure 5.

[0017] Now, the present invention will be described in detail.

[0018] The phospholipid derivative of the present invention is represented by the above formula (I). The residue of a phospholipid having phosphatidylethanolamine moiety for A, is not particularly limited so long as it is the one having a phosphatidylethanolamino group. However, it may preferably be a group of the following formula (II):



wherein each of R¹ and R² which are independent of each other, is a C₁₁-C₁₉ alkyl group such as a lauroyl group, a myristoyl group, a palmitoyl group or a stearoyl group, or a C₁₁-C₁₉ alkenyl group such as an oleyl group, and D is a single bond, or a C₁-C₁₁ linking group such as -C=(NH₂⁺)(CH₂)₀₋₁₀⁻, -CO(CH₂)₀₋₁₀⁻ or -CH₂(CH₂)₀₋₁₀⁻.


[0019] The linking group having a polyalkylene glycol moiety for B, is not particularly limited so long as it is the one having a polyalkylene glycol unit such as polyethylene glycol, polypropylene glycol, polytetramethylene glycol or polyhexamethylene glycol. However, it may preferably be a linking group of the following formula (III):



wherein each of J and L which are independent of each other, is a single bond, or a C₁-C₁₁ linking group such as -CO(CH₂)₀₋₁₀⁻, -(CH₂)₀₋₁₀CO⁻, -NHCO(CH₂)₀₋₁₀⁻, -(CH₂)₀₋₁₀CONH⁻, or -CH₂(CH₂)₀₋₁₀⁻, and PEG is a polyethylene glycol residue such as -(CH₂CH₂O)₁₁₋₄₅₅⁻.

[0020] Now, a process for producing the phospholipid derivative of the present invention will be described.

[0021] The phospholipid derivative of the present invention can be produced, for example, by reacting a lipid having a thiol group with a polyalkylene glycol having two maleimide groups.



In the above formulas, A and B are as defined above.

[0022] Now, the process will be described sequentially in detail.

1. Preparation of the phospholipid having a thiol group (hereinafter sometimes referred to simply as "the thiol-modified phospholipid")

[0023] The thiol-modified phospholipid can be obtained by introducing a thiol group to phosphatidylethanolamine by means of a known amino group-modifying reaction. Namely, it can be produced by dissolving a Traut reagent such as iminothiolane or a mercapto alkyl imidate and phosphatidylethanolamine in an organic solvent such as chloroform or chloroform/methanol (1/1 to 10/1) in the presence of a basic compound such as triethylamine or pyridine and reacting them at a temperature of from 20 to 40°C under a condition of an inner gas such as nitrogen gas or argon gas. Otherwise, it can be prepared by means of a thiol carboxylic acid disclosed in Japanese Unexamined Patent Publication No. 72067/1989. Or, it may be synthesized by bonding a compound inherently containing a sulfur atom, such as N-succin-

imidyl-3-(2-pyridyldithio)propionate, to phosphatidylethanolamine, followed by reducing with a large excess amount of a reducing agent such as 2-mercaptoethanol.

[0024] The phosphatidylethanolamine to be used here, i.e. the phospholipid having a phosphatidylethanolamine moiety, for A in the above formula (I), is not particularly limited and may, for example, be natural phosphatidylethanolamine derived from e.g. yolk, dioleoyl phosphatidylethanolamine, dimyristoyl phosphatidylethanolamine, dipalmitoyl phosphatidylethanolamine or distearoyl phosphatidylethanolamine, preferably dipalmitoyl phosphatidylethanolamine.

2. Preparation of the polyalkylene glycol having two maleimide groups (hereinafter sometimes referred to simply as "the maleimide PAG")

[0025] The process will be described in detail with respect to a case wherein the polyalkylene glycol moiety is polyethylene glycol (hereinafter sometimes referred to simply as "PEG").

[0026] The polyethylene glycol derivative having two maleimide groups can be obtained, for example, by dissolving diaminopolyethylene glycol (available from Nippon Oil and Fats or Sigma) and at least two mol times of a maleimide-modifying reagent such as N-(ϵ -maleimidocaproyloxy)succinimide in an organic solvent such as chloroform dehydrated by e.g. molecular sieve, in the presence of a basic compound such as triethylamine or pyridine and reacting them at a temperature of from 20 to 40°C under an atmosphere of an inner gas such as nitrogen gas or argon gas.

[0027] In addition to N-(ϵ -maleimidocaproyloxy)succinimide, the maleimide-modifying reagent may, for example, be N-succinimidyl 4-(p-maleimidophenyl)butyrate, N-succinimidyl 4-(p-maleimidophenyl)propionate or N-(γ -maleimido-butyryloxy)succinimide, which is commonly used for the preparation of a maleimide derivative of an amino group.

[0028] The average molecular weight of the PEG moiety is usually from 500 to 20000, preferably from 2000 to 10000, more preferably from 2000 to 5000. As such PEG, Sunbright® VFM5001 (Nippon Oil and Fats) or Polyoxyethylene-bisamine (Sigma) may specifically be mentioned.

3. Preparation of the compound of the present invention (hereinafter sometimes referred to simply as "M-PAG-PE")

[0029] M-PAG-PE can be prepared by adding and reacting the thiol-modified phospholipid dissolved in an organic solvent such as chloroform or chloroform/methanol (1/1 to 10/1) to the dimaleimide PAG dissolved in the same solvent in the presence of a basic compound such as triethylamine or pyridine at a temperature of from 0 to 40°C under an atmosphere of an inner gas such as nitrogen gas or argon gas. Here, the thiol-modified phospholipid is gradually added, and its total amount is usually at most an equimolar amount, preferably at most 1/2 mol of the maleimide PAG.

[0030] Then, hexane or petroleum ether is added to the reaction solution of M-PAG-PE to precipitate a PAG-containing compound. The precipitate collected by filtration is dried and then dissolved in distilled water at a concentration not lower than the concentration where M-PAG-PE itself forms particles (micell) in the aqueous solution. Insoluble matters are filtered off, and while maintaining the concentration at the above specified level, the solution is subjected to molecular weight fractionation by e.g. an ultrafiltration method, a dialysis method or a gel filtration method to obtain M-PAG-PE. At that time, impurities such as unreacted (excess) dimaleimide PAG are removed. Further, if necessary, purification by silica gel column chromatography may further be carried out.

[0031] The phospholipid derivative of the present invention thus obtained can be converted to a liposome by a conventional method. The liposome may be formed by a conventional lipid component such as phosphatidylcholine or cholesterol, and M-PAG-PE, or may be formed by mixing such a conventional lipid component, M-PAG-PE and another lipid derivative having a polyethylene glycol moiety as disclosed in e.g. Japanese Unexamined Patent Publication No. 249717/1989 or No. 149512/1990 or FEBS letters, 268,235 (1990).

[0032] The phosphatidylcholine useful as the lipid component is not particularly limited and may, for example, be natural phosphatidylcholine derived from e.g. yolk, dioleoyl phosphatidylcholine, dimyristoyl phosphatidylcholine, dipalmitoyl phosphatidylcholine or distearyl phosphatidylcholine.

[0033] The respective components are used in such proportions that per mol of the phosphatidylcholine, the cholesterol is used in an amount of from 0.3 to 1 mol, preferably from 0.4 to 0.6 mol, and M-PAG-PE is used in an amount of from 0.001 to 0.4 mol, preferably from 0.02 to 0.1 mol. Further, when another lipid derivative having a polyethylene glycol moiety is incorporated, such another lipid derivative is used in an amount of not more than 0.4 mol per mol of the phosphatidylcholine.

[0034] Then, the lipid mixture having the solvent removed, may, for example, be hydrated and emulsified by a homogenizer, followed by freezing-thawing to obtain a multilamella liposome (MLV). Further, it may be subjected to super sonic treatment, high speed homogenizing or press-filtration with a membrane having uniform pores (Hope M.J. et al, Biochimica et Biophysica Acta, 812, 55 (1985)) to obtain a single lamella liposome (SUV) and to adjust the particle size to a proper level. Here, a preferred particle size is from 20 to 300 nm, more preferably from 30 to 200 nm.

[0035] Various drugs may be loaded into such a liposome. As such a drug, an antitumor drug such as adriamycin, daunomycin, mitomycin, cisplatin, vincristine, epirubicin, methotrexate, SFU (5-fluorouracil) or acracinomycin, an

aminoglucoside such as gentamicin, a β -lactam antibiotic such as sulpenisillin, a toxin such as ricin A or diphtheria toxin, or an antisense RNA against human immunodeficiency virus (HIV), hepatitis B virus, hepatitis C virus or ras gene, may, for example, be mentioned.

[0036] Loading of the drug into the liposome can be conducted by hydrating the lipid with an aqueous drug solution in the case of a water-soluble drug, or by mixing the drug and the lipid in a volatile organic solvent, followed by distilling the solvent off and hydrating the mixture of the drug and the lipid to incorporate the drug into the liposome, in the case of a lipophilic drug.

[0037] Further, for the purpose of imparting a functionality to liposome, it is preferred to bond (introduce) a protein, a peptide, a saccharide, a hydrophilic polymer, etc. to the surface of the liposome, as mentioned above. In the present invention, it is preferred to bond (introduce) various proteins including antibodies or growth factors such as fibroblast growth factor (FGF) and epitheliocyte growth factor (EGF). Particularly preferred are antibodies. The antibodies are those (such as IgA, IgG and IgM) which are reactive with the tissues, cells, bacteria or virus to be treated. For example, polyclonal antibodies of various animals, a mouse monoclonal antibody, a human-mouse chimeric antibody and a human monoclonal antibody may be employed.

[0038] To bond such a protein to the liposome, the double bond of the maleimide group of the liposome and the thiol group of the protein can be utilized. Introduction of a thiol group to the protein can be conducted by a method wherein a compound is employed which is commonly used for thiol-modification of a protein and which is reactive with an amino group of the protein, such as N-succinimidyl-3-(2-pyridyldithio)propionate (SPDP) (Carlsson, J. et al., *Biochem. J.* 173, 723 (1978)) or iminothiolane, mercaptoalkylimide (Traut, R. R. et al., *Biochemistry*, 12, 3266 (1973)). In the case where the protein is an antibody, a method may be employed wherein endogenous dithiol groups in the cystine residues are reduced to thiol groups.

[0039] When IgG is employed among antibodies, it may be subjected to $F(ab')_2$ modification by treatment with an enzyme such as pepsin, followed by reduction with e.g. dithiothreitol to obtain Fab', whereupon thiol groups formed in Fab' are subjected to the bonding reaction with the liposome (Martin, F. J. et al., *Biochemistry*, 20, 4229 (1981)). In the case of IgM, J-chain may be reduced under a mild condition in accordance with a method of Miller et al. (*J. Biol. Chem.* 257, 286 (1965)), whereupon thiol groups of Fc moiety of IgMs thereby obtained, are subjected to the bonding reaction with the liposome.

[0040] The bonding of the liposome with such a protein can be accomplished by reacting them in a neutral buffer solution (pH 6.0 to 7.5) for from 2 to 16 hours.

[0041] To use the liposome of the present invention as a pharmaceutical composition, it may be administered by e.g. intravascular administration or local administration such as intravesical or intraperitoneal administration against various diseases. The dose may optionally be adjusted depending upon the pharmacological activities, the type of the drug, etc.

[0042] Now, the present invention will be described in further detail with reference to Examples. However, it should be understood that the present invention is by no means restricted to such specific Examples.

EXAMPLE 1

Preparation of M-PEG-PE

Preparation of thiol-modified phospholipid

[0043] 21.8 mg of iminothiolane (manufactured by Sigma Company) was added to 100 mg of dipalmitoyl phosphatidylethanolamine dissolved in 11 ml of a mixture of chloroform/methanol (6/5). Then, 50 μ l of triethylamine was further added thereto, and the mixture was stirred and reacted at room temperature in nitrogen gas until the ninhydrin reaction became negative. Formation of the thiol-modified phospholipid was confirmed by adding fluoresce maleimide (manufactured by Funakoshi) to a part of the reaction solution, reacting them at room temperature for 40 minutes and observing a fresh yellow fluorescent spot on a thin layer chromatography.

Preparation of dimaleimide PEG

[0044] 810 mg of diamino polyethylene glycol (Sunbright® VFM5001 (manufactured by Nippon Oil and Fats); average molecular weight: 5000) was dissolved in 5 ml of chloroform dehydrated by a molecular sieve, and 100 mg of N-(ϵ -maleimidocaproyloxy)succinimide and 50 μ l of triethylamine were added thereto. The mixture was stirred and reacted at room temperature in nitrogen gas. Formation of dimaleimide PEG was ascertained by confirming that the ninhydrin reaction became negative.

Bonding and purification

[0045] To 4 ml of the above dimaleimide PEG solution diluted to 30 ml with chloroform, 10 ml of the above thiol-modified phospholipid solution was gradually added, and the mixture was stirred at room temperature for 3 hours under a nitrogen gas condition. To 20 ml of the reaction solution thus obtained, an adequate amount of hexane was added to form a precipitate containing M-PEG-PE. The precipitate was vacuum-dried, whereupon the weight was 330 mg. It was dissolved in 10 ml of distilled water, and insoluble substances were removed by centrifugal separation of 16000 X g for 5 minutes. Further, the same amount of distilled water was added, and concentration-filtration was repeated by means of Centricon 100 (manufactured by Amicon) equipped with an ultra filter membrane with a molecule weight fraction of 100k. By this purification process, PEG not combined with the lipid derivative, was filtered off.

Measurement by NMR

[0046] As shown by the ¹H-NMR chart of the desired product in Figure 1, a signal of 1.54 ppm of the alkyl chain proton of the phospholipid, a signal of 3.57 ppm attributable to -CH₂CH₂O- of PEG and a signal of 6.61 ppm attributable to the double bond of the maleimide, were confirmed.

Reference Example 1

[0047] As shown in Example 1, the phospholipid derivative of the present invention was considered to behave as a molecular aggregate in the aqueous solution. Therefore, the form of M-PEG-PE in the aqueous solution was studied.

[0048] M-PEG-PE dissolved in distilled water at a concentration of 0.5 mg/ml, was measured by a dynamic light scattering method (ELS-800, manufactured by Otsuka Denshi), whereby particles of 24.8 nm (g (GAMMA) distribution) were observed.

EXAMPLE 2Measurement of maleimide

[0049] The maleimide content of M-PEG-PE obtained in Example 1 was determined by adding cysteine to the aqueous solution and quantitatively analyzing the SH amount consumed by the maleimide by means of 4,4'-dithiopyridine. Namely, an aqueous solution containing 1.1 mg/ml of M-PEG-PE was mixed in the following proportion, and the mixture was reacted at room temperature for 30 minutes.

M-PEG-PE	100μl
1mM EDTA-containing 0.1M phosphate buffer (pH 6.0)	800μl
0.5mM cysteine	100μl

[0050] After the reaction, 40 μl of 5mM 4,4'-dithiopyridine was added to 960 μl of the above solution, and the maleimide content was determined by comparing the change in the absorbance at 324 nm by the color developed by the reaction with the remaining cysteine, with that of the control sample (a molar absorptance coefficient of the developed color of 19800/M was employed).

[0051] As a result, a maleimide amount of 0.17 μmol per mg of M-PEG-PE was detected.

EXAMPLE 3Preparation of liposome containing M-PEG-PE

[0052] 50 mg of dipalmitoyl phosphatidylcholine, 14.6 mg of cholesterol, 10.7 mg of M-PEG-PE and 0.16 mg of FITC-DPPE (1,2-Dihexadecanoyl-sn-glycero-3-phospho[N-(5-fluoresceinethiocarbonyl)]ethanolamine, manufactured by Sigma) as a fat-soluble marker, were dissolved uniformly in chloroform, and the solvent was removed by an evaporator to form a lipid film. Further, the film was dried under reduced pressure by a vacuum pump for 2.5 hours, and then a 0.1M phosphate buffer solution (pH 6.0) and 1 ml of 1mM EDTA were added thereto, the mixture was stirred and hydrated by a vortex mixer. Then, freezing-thawing was repeated five times by means of liquid nitrogen and warm bath of 65°C, to obtain a milky white multilamella liposome (MLV).

[0053] Then, 0.5 ml of the above MLV was adjusted to 1 ml with the above buffer solution and subjected to supersonic treatment for 10 minutes by a Probe-type sonicator (Sonifier 450, manufacture by Branson Company) at an output of 20%, to obtain a transparent small diameter liposome (SUV solution). Figure 2 shows the particle size distribution of the liposome thus obtained, as measured by a dynamic light scattering method. it is shown that there was no inclusion of particles having a diameter of more than 1 μm .

COMPARATIVE EXAMPLE

[0054] MLV was prepared in the same manner as in Example 3 except that the lipid composition did not contain M-PEG-PE. Supersonic treatment for 10 minutes was repeated twice in the same manner, and then the particle size distribution was measured by a dynamic light scattering method. The results are shown in Figure 3. Particles having a diameter of more than 1 μm were included, thus indicating that no adequate micronization was accomplished.

EXAMPLE 4

Bonding of an antibody to the M-PEG-PE-containing liposome

[0055] To an antitumor human monoclonal antibody (IgG; GAH disclosed in EP 0520499 A), 1/40 mol amount of pepsine (Cooper Biomedical) in 0.1M acetic acid buffer solution (pH 4.0), was added, and the mixture was reacted at 37°C over night for digestion to obtain $F(ab')_2$.

[0056] Further, by chromatography separation with a cation exchange resin (Mono S, manufactured by Pharmacia), $F(ab')_2$ was isolated. The preparation was conducted by a linear gradient from 0M to 1.0M NaCl in a 0.1M acetic acid buffer solution (pH 4.0), to obtain $F(ab')_2$.

[0057] The buffer solution was changed to a 50mM phosphate buffer solution (pH 7.5) and 1mM EDTA in a PD-10 column (manufacture by Pharmacia) to obtain a solution having an antibody concentration of 2.4 mg/ml. Then, iminothiolane (3 mg/ml) was added thereto in an amount corresponding to 4 mol times of the antibody, and the mixture was reacted at 37°C for one hour. Unreacted iminothiolane was removed by demineralization by a PD-10 column equilibrated with a 0.1M phosphate buffer solution (pH 6.0) and 1mM EDTA, to obtain 1.9 mg/ml of a thiol-modified antibody.

[0058] To 0.7 ml of this antibody, 0.42 ml of the SUV liposome obtained in Example 3, was added, and the mixture was shaken at room temperature over night to obtain an immunoliposome.

EXAMPLE 5


Reactivity to the target cells

[0059] Using human gastric cancer cell line MKN 45 (having a reactivity with the antibody used in Example 4) which was cultured on a slide chamber (Lab-Tek® chamber, manufactured by Nunc, Inc.) and fixed by paraformaldehyde, the reactivity of the immunoliposome prepared in Example 4, was confirmed. A reaction solution comprising 50 μl of the liposome solution, 150 μl of a human serum and 50 μl of a 10 mM phosphate buffer solution (pH 7.4) and 0.15M NaCl, was added to the cells, and the mixture was incubated at 37°C for 30 minutes. After washing with the same buffer solution, fluorescence of FITC-DPPE (as mentioned above) introduced as a marker, was observed by a fluorescence microscope (Confocal microscope adoptor VX100, manufactured by Newport). The respective fluorescence microscopic photographs are shown in Figure 4 (antibody-bonded liposome), Figure 5 (non antibody-bonded liposome prepared in Comparative Example) and Figure 6 (Luminous field image of Figure 5). As compared with the liposome used as control, high reactivity of the immuno liposome of the present invention to MKN45 cells was confirmed.

[0060] The phospholipid derivative of the present invention is useful as a phospholipid component constituting a liposome, and the liposome employing the phospholipid derivative has a polyalkylene glycol moiety, whereby non-specific uptake by a reticuloendothelial system such as liver or spleen can be suppressed and at the same time the liposome can be readily bonded to a protein having thiol moiety. Further, by means of the phospholipid derivative of the present invention, the liposome can readily be micronized.


Claims

1. A phospholipid derivative of the following formula (I):



10 wherein A is a residue of a phospholipid having a phosphatidylethanolamine moiety, and B is a linking group having a polyalkylene glycol moiety.

2. The phospholipid derivative according to Claim 1, wherein the residue of a phospholipid having a phosphatidylethanolamine moiety is of the following formula (II):




30 wherein each of R¹ and R² which are independent of each other, is a C₁₁ - C₁₉ alkyl group or a C₁₁-C₁₉ alkenyl group, and D is a single bond, or a C₁-C₁₁ linking group.

3. The phospholipid derivative according to Claim 1, wherein the linking group having a polyalkylene glycol moiety is of the following formula (III):



40 wherein each of J and L which are independent of each other, is a single bond, or a C₁-C₁₁ linking group, and PEG is a polyethylene glycol residue.

4. A liposome containing a phospholipid derivative of the following formula (I):




wherein A is a residue of a phospholipid having a phosphatidylethanolamine moiety, and B is a linking group having a polyalkylene glycol moiety.

- 55 5. The liposome according to Claim 4 having a thiol group-imparted protein bonded via the phospholipid derivative.
6. The liposome according to Claim 4 having a thiol group-imparted protein bonded via a double bond of a maleimide group of the phospholipid derivative.

7. The liposome according to Claim 4 having a drug loaded.
8. The liposome according to Claim 7, wherein the drug is an antitumor drug.
9. The liposome according to Claim 8, wherein the antitumor drug is selected from the group consisting of adriamycin, daunomycin, mitomycin, cisplatin, vincristine, epirubicin, methotrexate, 5-fluorouracil and acracinomycin.
10. The liposome according to any one of Claims 5 to 9, wherein a protein having a thiol group is an antibody wherein endogenous dithiol groups in cistine residues thereof having been reduced to thiol group.
11. A pharmaceutical composition comprising an effective amount of the liposome according to Claim 7, and a pharmaceutically acceptable carrier thereof.


Patentansprüche

1. Phospholipid-Derivat der folgenden Formel (I):



worin A ein Phospholipidrest mit einer Phosphatidylethanolamin-Einheit ist, und B eine Bindungsgruppe mit einer Polyalkylenglykol-Einheit ist.

2. Phospholipid-Derivat nach Anspruch 1, wobei der Phospholipidrest mit einer Phosphatidylethanolamin-Einheit der folgenden Formel (II) entspricht:




worin jedes von R¹ und R², welche voneinander unabhängig sind, eine C₁₁-C₁₉-Alkylgruppe oder C₁₁-C₁₉-Alkenylgruppe ist, und D eine Einfachbindung oder eine C₁-C₁₁-Bindungsgruppe ist.

3. Phospholipid-Derivat nach Anspruch 1, wobei die Bindungsgruppe mit einer Polyalkylenglykol-Einheit der folgenden Formel (III) entspricht:



worin jedes J und L, welche voneinander unabhängig sind, eine Einfachbindung oder eine C₁-C₁₁-Bindungsgruppe ist, und PEG ein Polyethylenglykolrest ist.

4. Liposom, enthaltend ein Phospholipid-Derivat der folgenden Formel (I):



(I)

5

10

15

25

30

worin A ein Phospholipidrest mit einer Phosphatidylethanolamin-Einheit ist, und B eine Bindungsgruppe mit einer Polyalkylenglykol-Einheit ist.

5. Liposom nach Anspruch 4 mit einem über das Phospholipid-Derivat gebundenen Protein, das mit einer Thiolgruppe versehen ist.

6. Liposom nach Anspruch 4 mit einem über eine Doppelbindung einer Maleimidgruppe des Phospholipid-Derivats gebundenen Protein, das mit einer Thiolgruppe versehen ist.

7. Liposom nach Anspruch 4, das mit einem Arzneimittel beladen ist.

8. Liposom nach Anspruch 7, wobei das Arzneimittel ein Antitumor-Arzneimittel ist.

9. Liposom nach Anspruch 8, wobei das Antitumor-Arzneimittel aus der Adriamycin, Daunomycin, Mitomycin, Cisplatin, Vincristin, Epirubicin, Methotrexat, 5-Fluorouracil und Acracinomycin umfassenden Gruppe gewählt ist.


10. Liposom nach mindestens einem der Ansprüche 5 bis 9, wobei ein eine Thiolgruppe aufweisendes Protein ein Antikörper ist, wobei endogene Dithiolgruppen in Cystinresten hiervon zur Thiolgruppe reduziert worden sind.

11. Pharmazeutische Zusammensetzung, umfassend eine wirksame Menge des Liposoms nach Anspruch 7 und einen pharmazeutisch annehmbaren Träger hierfür.

Revendications

35

1. Dérivé de phospholipide de formule (I) suivante :



(I)

40

45


50

55

dans laquelle A est un résidu d'un phospholipide ayant un fragment phosphatidyléthanolamine, et B est un groupe de liaison ayant un fragment polyalkylène glycol.

2. Dérivé de phospholipide selon la revendication 1, dans lequel le résidu d'un phospholipide ayant un fragment phosphatidyléthanolamine répond à la formule (II) suivante :

(II)



dans laquelle chacun de R¹ et R², qui sont indépendants l'un de l'autre, est un groupe alkyle en C₁₁ à C₁₉ ou un groupe alcényle en C₁₁ à C₁₉, et D est une liaison simple, ou un groupe de liaison en C₁ à C₁₁.


3. Dérivé de phospholipide selon la revendication 1, dans lequel le groupe de liaison ayant un fragment polyalkylène-glycol répond à la formule (III) suivante :



(III)

dans laquelle chacun de J et L, qui sont indépendants l'un de l'autre, est une liaison simple, ou un groupe de liaison en C₁ à C₁₁, et PEG est un résidu de polyéthylène-glycol.

4. Liposome contenant un dérivé de phospholipide de formule (I) suivante :



(I)

dans laquelle A est un résidu d'un phospholipide ayant un fragment phosphatidyléthanolamine, et B est un groupe de liaison ayant un fragment polyalkylène-glycol.

5. Liposome selon la revendication 4, ayant une protéine, à laquelle est conférée un groupe thiol, qui est liée par l'intermédiaire du dérivé de phospholipide.
6. Liposome selon la revendication 4, ayant une protéine, à laquelle est conférée un groupe thiol, qui est liée par l'intermédiaire d'une double liaison d'un groupe maléimide du dérivé de phospholipide.
7. Liposome selon la revendication 4, qui est chargé d'un médicament.
8. Liposome selon la revendication 7, dans lequel le médicament est un médicament antitumoral.
9. Liposome selon la revendication 8, dans lequel le médicament antitumoral est choisi dans le groupe constitué par l'adriamycine, la daunomycine, la mitomycine, le cisplatine, la vincristine, l'épirubicine, le méthotrexate, le 5-fluorouracile et l'acracinomycline.
10. Liposome selon l'une quelconque des revendications 5 à 9, dans lequel une protéine ayant un groupe thiol est un anticorps dans lequel des groupes dithiol endogènes dans des résidus de cystine de celui-ci ont été réduits en groupes thiol.
11. Composition pharmaceutique comprenant une quantité efficace du liposome selon la revendication 7 et un support acceptable en pharmacie pour celui-ci.

FIGURE 1




FIGURE 2




FIGURE 3




FIGURE 4




FIGURE 5




FIGURE 6

